

# 08 Wood Tex Patina

## Product properties

Colourless treatment which reacts with the wood and gives a yellow-brown/pink tone. After 6-8 weeks, the surface changes to a silver-grey transparent surface. Creates a physical barrier that inhibits mould and mildew growth on the surface and imparts effective flame-retardant properties. Used as a pre-treatment prior to final treatment with Wood Tex Sealer.

- Environmentally friendly silicon technology
- Flame retardant
- Maximum durability



## Product use

Pressure-impregnated fully exposed wood such as outdoor decks.  
The surface must be new or totally stripped.

## Substrate

Must be new or completely stripped, absorbent, clean, dry, solid and suitable for paint treatment. Insufficiently protected cross-cut wood, water traps or risk of water accumulation must not occur. The moisture level in the wood prior to paint treatment max. 20%.  
New pressure-impregnated wood must be allowed to dry for 4-6 months prior to treatment.

## Treatment

Wood stain, paint and decayed wood fibres must be completely removed by cleaning and sanding. Remove dirt, filth, grease and chalking material with Terrace Cleaner. Algae, mould and mildew must be removed by cleaning with Facade Anti-green. Final treatment with Flügger 08 Wood Tex Sealer: after 4-6 hours.

## Application

Brush or roller.  
Apply two times with 1 hour drying time between applications and work well into the wood. Apply wet-on-wet and carefully remove any excess liquid.  
The transition to gray becomes uneven if sun and rain cannot hit. The wood protection can be used in these areas, but the transition to gray takes longer.  
Condensation must not form.  
Avoid working in direct sunlight.  
The surface must not be exposed to frost or rain for at least 24 hours after completing treatment.

## Expected result

Silver-grey and transparent surface that leaves the wood's vein structure visible.  
The appearance and durability of the surface depends on the wood quality, structure, application and exposure.

# Cleaning and maintenance

Loose wood fibers are removed with a brush.

Dirt, grease and chalking material should be removed using Facade Clean.

Algae, mould and mould growth are removed by cleaning with Facade Anti-green.

Maintain with Flügger 08 Wood Tex Sealer every two years or as needed.

## Please note!

Protect freshly painted surface from adverse weather conditions.

Take appropriate measures against the effects of moisture and rainfall on freshly painted surfaces.

The surface achieves maximum robustness when fully cured.

## Environmental information

Clean off the paint from tools and wash them with water. Bring remains of fluent paint to the local recycling centre.

Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

**Storage:** Cool, frost free and tightly closed

## Technical Data

Product Type	Impregnation
Density (kgs/l)	1.0
Nominal spreading rate (m <sup>2</sup> /ltr.)	5
Short Spreading rate (m <sup>2</sup> /l)	3
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Recoatable at 20° C, 60 % RH (Hours)	1
Dilution	Do not dilute
Cleaning of Tools etc.	Water

### Current TDS Version

January 2024

### Replaces TDS Version

June 2023