

Plaster for Stucco

Properties

Type: Gypsum, stucco gypsum. Burnt gypsum (calcium sulphate). In dried condition gypsum is faintly soluble with water. It is therefore not suitable exterior or under moist conditions.

Use

Suitable mixed with a little water for repair of minor cracks, holes and cast items etc. on ceiling and wall.

Pour slowly 3 vol. parts gypsum in a bucket with 1 vol. part water and stir to uniform consistency.



Storage: Cool, frost-free and tightly closed

Technical Data

Product Type	Plaster & Sealant
Density (kgs/l)	1.02
Min. working temp. during application and drying/curing	Min. +10°C
Recoatable at 20° C, 60 % RH (Hours)	1
Cleaning of Tools etc.	Water

Current TDS Version

July 2022

Replaces TDS Version

February 2008